

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
24 March 2005 (24.03.2005)

PCT

(10) International Publication Number  
**WO 2005/026403 A1**

(51) International Patent Classification<sup>7</sup>:  
4/18, B44C 5/04, C25D 11/00, 17/14

C23C 4/08,

(21) International Application Number:  
PCT/IB2004/003035

(22) International Filing Date:  
17 September 2004 (17.09.2004)

(25) Filing Language: Italian

(26) Publication Language: English

(30) Priority Data:  
PI2003A000070 17 September 2003 (17.09.2003) IT

(71) Applicant and

(72) Inventor: **TURRINI, Luigi** [IT/IT]; Via F. Cavallotti, 21,  
I-41100 Modena (IS).

(74) Agent: **CELESTINO, Marco?**; Viale Giovanni Pisano,  
31, I-56123 Pisa (IT).


(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:  
— with international search report

[Continued on next page]

(54) Title: METHOD FOR MAKING A METAL DECORATIVE EFFECT ON THE SURFACE OF AN OBJECT



(57) Abstract: Method for metallizing the surface of an object, for example a plate (20) of ceramics or other inert material, of stone, wood, plastics. The process begins with the location of the plate (20) in the vicinity of means for delivering molten metal (1), towards which a metal supply is fed in the form of metal wires (2 and 3) for example through guided by sheaths (4). In the means for melting (1) and in particular at melting site (15) the melting occurs of the metal source (2 or 3). This can be carried out by discharging an electrical arch between two electrodes, or between an electrode and a metal wire that in this case works as second electrode, or still discharging an electrical arch directly between the metal wires (2 and 3). Alternatively, the melting of the metal wire (2 or 3), can be executed using a combination of a 20 current of gas fuel and a current of a comburent gas burning at high temperature at the melting site. (figure 1)



— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*